

PRODUCT

INFORMATION



PRATT & LAMBERT PAINTS

RedSeal® Exterior Oil Gloss House & Trim S4900 / D4900 Series

DESCRIPTION:

RedSeal Exterior Oil Gloss House & Trim is formulated to provide maximum durability through all types of weather. RedSeal Exterior Oil Gloss House & Trim flows on easily and dries evenly to a smooth, attractive finish.

USES:

Recommended for exterior use on surfaces such as wood, siding, trim, doors, primed downspouts, gutters, sashes and frames.

SIZES: Gallons, Quarts

COLORS:

Super One-Coat White, Gloss Black, and all Base 1, Base 2 and Base 3 Colors.

RECOMMENDED SYSTEMS:

NEW WORK:

WOOD

Spot prime knots with SUPRIME Int/Ext Odorless Stain Blocker
1 coat of SUPRIME Exterior Alkyd Wood Primer
1 or 2 coats of RedSeal Exterior Oil Gloss House & Trim

METAL

1 coat of Tech-gard Alkyd Metal Primer or Tech-gard Acrylic Prime or Finish
1 or 2 coats of RedSeal Exterior Oil Gloss House & Trim

PLASTER

New: After dry, 1 coat of SUPRIME Int/Ext 100% Acrylic Multi-Purpose Primer
Old: (>60 days), 1 coat of SUPRIME Exterior Alkyd Wood Primer
1 or 2 coats of RedSeal Exterior Oil Gloss House & Trim

MASONRY OR AGGREGATE BLOCK

1 coat of SUPRIME Int/Ext 100% Acrylic Multi-Purpose Primer
1 or 2 coats of RedSeal Exterior Oil Gloss House & Trim
(For a filled effect, use PRO-HIDE Silver Heavy Duty Latex Block Filler as a first coat)

EXTERIOR DRYWALL

1 coat of SUPRIME Int/Ext 100% Acrylic Multi-Purpose Primer
1 or 2 coats of RedSeal Exterior Oil Gloss House & Trim

REPAINT:

Spot prime bare areas with appropriate primer
1 or 2 coats of RedSeal Exterior Oil Gloss House & Trim

PRODUCT DETAIL:

Vehicle:	Alkyd
Sheen:	Gloss (80+ @ 60°)
% Solids:	By Weight: 66% By Volume: 52%
Wt./Gallon:	9.4 lbs.
Flashpoint:	102°F
VOC Level:	Max 380 g/l (3.16 lbs./gal.)
Thinner*:	Mineral Spirits
Cleanup:	Mineral Spirits
Dry Time:	@ 77°F (25°C) 50% RH: To Touch: 6.0 Hours Recoat: 24.0 Hours Use: 24.0 Hours
Rec. Film Thickness:	Dry: 1.5 Mils Wet: 3.0 Mils
Coverage:	600 sq. ft./gallon

APPLICATION:

Brush:	Natural Bristle
Roller:	3/8" nap cover
Pad:	Standard
Conv. Spray:	Thin with up to 1 pint Mineral Spirits*
Airless Spray:	At package consistency

* Do not reduce in municipalities, counties, states or provinces where solvent addition will cause VOC limits to be exceeded. Follow all manufacturer's guidelines when working with solvents.

Technical Information Line:
1-800-BUY-PRAT (1-800-289-7728)
www.prattandlambert.com

SURFACE PREPARATION:

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

General

Remove all surface contamination by washing with appropriate cleaner, rinse thoroughly and allow to dry. Scrape and sand peeled or checked paint to a sound surface. Sand glossy surfaces dull. Seal stains from water, smoke, ink, pencil, grease, etc. with Pratt & Lambert SUPRIME Int/Ext 100% Acrylic Multi-Purpose Primer.

Drywall

Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.

Exterior Drywall

Fill cracks and nail holes with an exterior grade patching paste/spackle and sand smooth. Remove all sanding dust.

Masonry, Concrete, Cement, Block, Stucco, Brick

Allow new surfaces to cure according to supplier's recommendations, or at least 7 days. Allow stucco to cure at least 30 days. If painting cannot wait 30 days, or surfaces have a pH from 9 to 13, allow surface to dry 5-7 days and use PRO-HIDE Gold Acrylic Concrete and Stucco Primer or PRO-HIDE Gold Acrylic Surface Conditioner as a first coat.

Plaster

Bare plaster must be cured and hard. Treat textured, soft, porous, or powdery plaster with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.

Wood

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.

Aluminum and Galvanized Steel

Wash with appropriate cleaner to remove any oil, grease, or other surface contamination. Remove all corrosion with sandpaper, steel wool, or other abrading method. Prime with a latex primer - **do not apply alkyd products to galvanized surfaces.**

Steel

Remove rust and mill scale using sandpaper, steel wool, or other abrading method. Prime bare steel the same day as cleaned.

Mildew

Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. **DO NOT ADD DETERGENTS OR AMMONIA TO THE BLEACH/WATER SOLUTION.**

CLEANUP INFORMATION:

Clean spills and spatters immediately with mineral spirits. Clean tools immediately after use with mineral spirits. Follow manufacturer's safety recommendations when using all solvents.

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of Pratt & Lambert Paints. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Pratt & Lambert dealer or representative to obtain the most recent Product Data Sheet.



PRATT & LAMBERT PAINTS

APPLICATION:

Do not apply at air or surface temperatures below 50°F or when air or surface temperatures may drop below 50°F within 48 hours. No reduction necessary.

Brush

Use a natural bristle brush.

Roller

Use a 3/8" nap lambswool roller cover.

Spray-Airless

Pressure 2000 psi
Tip015 - .019

Spray-Conventional

Thin with up to 1 pint of mineral spirits
Air Pressure 40-60 psi
Fluid Pressure 10-20 psi
Cap/Tip 704/FX

TIPS TO IMPROVE

PERFORMANCE:

- Clean the surface thoroughly.
- Prepare the substrate to create a uniform surface.
- Patch cracks, crevices, and through-wall openings using proper sealant or patch.
- Fill voids and openings around windows and doors using proper sealant or patch.
- Caulk as needed using quality latex or siliconized latex caulk or sealant.

MAINTENANCE:

Wait at least two weeks before washing the dry paint film. When removing stains, dirt, and marks, use a soft cloth or sponge with water or other general purpose household cleaner. Penetrating stains and marks can be removed either by applying a solution of household bleach in water and then rinsing with clean water; or, by carefully using an abrasive cleaner and water.

CAUTIONS:

For exterior use only.
Not for use on horizontal surfaces (floors, roofs, decks, etc.) or where water will collect.