

# PRODUCT

## INFORMATION



PRATT & LAMBERT PAINTS

### PRO-HIDE® Gold Exterior Elastomeric Coating

Z6000 - White

Z6093 - Deep Base

#### DESCRIPTION:

PRO-HIDE Gold Exterior Elastomeric is a high build, flexible, weather resistant coating. When properly applied to tilt-up, precast or poured-in-place concrete, CMU or stucco surfaces, it will protect against wind-driven rain.

#### USES:

Recommended for properly prepared concrete, block, stucco and other cementitious vertical surfaces. It may be used on new and re-paint work.

#### REQUIREMENTS:

A two-coat application is recommended for optimal results. **A total dry film thickness of 12-15 mils with fewer than 10 pinholes per square foot is required for a waterproofing system.**

#### SIZES:

Fives, Gallons

#### COLORS:

White (may be tinted with up to 4 oz. of colorant)

Deep Base (may be tinted with up to 12 oz. of colorant)

#### RECOMMENDED SYSTEMS:

##### NEW WORK:

##### CONCRETE, STUCCO

1 coat of PRO-HIDE Gold Exterior Acrylic Concrete & Stucco Primer

2 coats of PRO-HIDE Gold Exterior Elastomeric

##### CONCRETE BLOCK, CMU, SPLIT-FACE BLOCK

1 coat PRO-HIDE Gold Exterior Acrylic Surface Conditioner

2 coats of PRO-HIDE Gold Exterior Elastomeric

##### REPAINT:

1 coat PRO-HIDE Gold Exterior Acrylic Surface Conditioner

2 coats of PRO-HIDE Gold Exterior Elastomeric

#### PRODUCT DETAIL:

<b>Vehicle:</b>	100% Acrylic Latex
<b>Sheen:</b>	5-10 units @ 85°
<b>% Solids:</b>	By Weight: 60% ± 2% By Volume: 46% ± 2%
<b>Wt./Gallon:</b>	11.25 lbs.
<b>Flashpoint:</b>	499°F
<b>VOC Level:</b>	100 g/l, 0.84 lb/gal
<b>Thinner:</b>	Water
<b>Cleanup:</b>	Soap and water
<b>Dry Time:</b>	@ 77°F (25°C) 50% RH: To Touch: 4.0 Hours To Recoat: 24.0 Hours
<b>Coverage:</b>	100 sq. ft./gallon @ 16 mils wet; 7.7 mils dry

#### APPLICATION:

<b>Brush:</b>	Nylon /Polyester
<b>Roller:</b>	1/2" nap - 1-1/2" nap
<b>Conv. Spray:</b>	Do not reduce
<b>Airless:</b>	Do not reduce

#### Physical Properties:

Elongation Break - 350%
(Test method - ASTM D412)
Tensile Strength - 368
(Test method - ASTM D412)
Vapor Transmission Range - 17.8 Perms
(Test method - ASTM E96)
Accelerated Weathering - 2000 Hours +
(Test method - ASTM C26 or D822)
Wind-Driven Rain - Passes 98 MPH
(Test method - TT-C-555B; 4.4.7)
Fungus/Mildew Resistance - No growth per
TT-C-555B (Test method - ASTM D3274/3273)
Flexibility - Meets standards
(Test method - ASTM D522)

#### Technical Information Line:

1-800-BUY-PRAT (1-800-289-7728)  
[www.prattandlambert.com](http://www.prattandlambert.com)

8.09

## SURFACE PREPARATION:

**WARNING!** Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

### General

Remove all surface contamination by washing with appropriate cleaner, rinse thoroughly and allow to dry. Scrape and sand peeled or checked paint to a sound surface. Sand glossy surfaces dull.

### Masonry, Concrete, Cement, Block, Stucco, Brick

Allow new surfaces to cure according to supplier's recommendations; at least 30 days. Remove all surface contamination (dirt, dust, grease, oil, peeling paint, heavy chalk, efflorescence, laitance, concrete dust, etc.) by washing with an appropriate cleaner; if necessary, pressure wash with a minimum of 2100 psi, rinse thoroughly and allow to dry to less than 15% moisture content. Remove all form release and curing agents. On tilt-up and poured-in-place concrete, commercial detergents or sandblasting may be necessary to remove sealers, release compounds, and to provide an anchor pattern. Repair or replace damaged or defective substrates as needed. Allow brick to age for 1 year prior to coating.

### Caulking

Fill gaps between walls, ceilings, moldings, and other trim with latex or siliconized latex caulk after priming the surface.

### Mildew

Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. **DO NOT ADD DETERGENTS OR AMMONIA TO THE BLEACH/WATER SOLUTION.**

## CLEANUP INFORMATION:

Clean spills and splatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using all solvents.



## PRATT & LAMBERT PAINTS

### APPLICATION:

Apply at temperatures above 50°F.  
Do not reduce.

#### Brush

Use a nylon/polyester brush.

#### Roller

Use a 1/2" - 1-1/2" nap synthetic roller cover.

#### Spray—Airless

Pressure ..... 2300 psi  
Tip ..... .021 - .029

#### Spray—Conventional

Air Pressure ..... 50-60 psi  
Fluid Pressure ..... 20-40 psi  
Cap/Tip ..... 704/FX

### TIPS TO IMPROVE

#### PERFORMANCE:

- Clean the surface thoroughly.
- Prepare the substrate to create a uniform surface.
- Patch cracks, crevices, and through-wall openings using proper sealant or patch.
- Fill voids and openings around window and doors using proper sealant or patch.
- Caulk as needed using quality latex or siliconized latex caulk or sealant.

#### MAINTENANCE:

To assure maximum washability and durability, wait at least two weeks before washing the dry paint film. When removing stains, dirt, and marks, use a soft cloth or sponge with water or other general purpose household cleaner. Penetrating stains and marks can be removed either by applying a solution of household bleach in water and then rinsing with clean water; or, by carefully using an abrasive cleaner and water.

#### CAUTIONS:

For exterior use only.  
Protect from freezing.  
Do not shake excessively.  
Not for use on roofs, floors, or decks.  
Not for use on horizontal surfaces or where water will collect.