

# PRODUCT

---

## INFORMATION



PRATT & LAMBERT PAINTS

### PRO-HIDE® Gold Interior/Exterior Acrylic Concrete & Stucco Primer Z6300

#### DESCRIPTION:

PRO-HIDE Gold Int./Ext. Acrylic Concrete & Stucco Primer has been manufactured for above grade masonry surfaces where a high performance primer is needed. It is efflorescence and alkali resistant and will increase and reinforce the performance of latex paints. It can be used on concrete, concrete block, brick and stucco. The surface onto which the coating is applied may have a pH of 6 to 13.

#### USES:

Recommended for properly prepared concrete, concrete block, brick and stucco.

**SIZES:** Fives, Gallons

**COLORS:** White

#### RECOMMENDED SYSTEMS:

##### NEW WORK:

##### MASONRY, AGGREGATE BLOCK, STUCCO

1 coat of PRO-HIDE Gold Int./Ext. Acrylic Concrete & Stucco Primer  
1 or 2 coats of selected Latex Finish

##### PLASTER

1 coat PRO-HIDE Gold Int./Ext. Acrylic Concrete & Stucco Primer  
1 or 2 coats of selected Latex Finish

##### REPAINT:

1 coat PRO-HIDE Gold Int./Ext. Acrylic Concrete & Stucco Primer  
1 or 2 coats of selected Latex Finish

#### PRODUCT DETAIL:

<b>Vehicle:</b>	100% Acrylic Latex
<b>Sheen:</b>	Flat (0-10 @ 85°)
<b>% Solids:</b>	By Weight: 53% By Volume: 40%
<b>Wt./Gallon:</b>	10.7 lbs.
<b>Flashpoint:</b>	201°F
<b>VOC Level:</b>	130 g/l, 1.08 lb/gal
<b>Thinner:</b>	Water
<b>Cleanup:</b>	Soap and water
<b>Dry Time:</b>	@ 77°F (25°C) 50% RH: To Touch: 4.0 Hours To Recoat: 24.0 Hours
<b>Coverage:</b>	200 sq. ft./gallon @ 8 Mils wet; 3.2 Mils dry

#### APPLICATION:

<b>Brush:</b>	Nylon /Polyester
<b>Roller:</b>	1/2" nap - 1 1/2" nap
<b>Pad:</b>	Not recommended
<b>Conv. Spray:</b>	Thin with up to 1 pint water
<b>Airless Spray:</b>	At package consistency

Technical Information Line:  
1-800-BUY-PRAT (1-800-289-7728)  
[www.prattandlambert.com](http://www.prattandlambert.com)

## SURFACE PREPARATION:

**WARNING!** Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

### General

Remove all surface contamination by washing with appropriate cleaner, rinse thoroughly and allow to dry. Scrape and sand peeled or checked paint to a sound surface. Sand glossy surfaces dull.

### Masonry, Concrete, Cement, Block, Stucco, Brick

Allow new surfaces to cure according to supplier's recommendations; at least 7 days.

Remove all surface contamination (dirt, dust, grease, oil, peeling paint, heavy chalk, efflorescence, laitance, concrete dust, etc.) by washing with an appropriate cleaner; if necessary, pressure wash with a minimum of 2100 psi, rinse thoroughly and allow to dry.

Remove all form release and curing agents. On tilt-up and poured-in-place concrete, commercial detergents or sandblasting may be necessary to remove sealers, release compounds, and to provide an anchor pattern.

Repair or replace damaged or defective substrates as needed.

Allow brick to age for 1 year prior to coating.

### Plaster

Bare plaster must be cured and hard. Treat textured, soft, porous, or powdery plaster with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.

### Caulking

Fill gaps between walls, ceilings, crown moldings, and other trim with latex or siliconized latex caulk after priming the surface.

### Mildew

Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. **DO NOT ADD DETERGENTS OR AMMONIA TO THE BLEACH/WATER SOLUTION.**

## CLEANUP INFORMATION:

Clean spills and splatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.



## PRATT & LAMBERT PAINTS

### APPLICATION:

Apply at temperatures above 50°F.  
Do not reduce.

#### Brush

Use a nylon/polyester brush.

#### Roller

Use a 1/2" - 1-1/2" nap synthetic roller cover.

#### Spray-Airless

Pressure ..... 2500 psi  
Tip ..... .019 - .021

#### Spray-Conventional

*Thin with up to 1 pint of water*

Air Pressure ..... 40-60 psi  
Fluid Pressure ..... 10-20 psi  
Cap/Tip ..... 704/FX

### CAUTIONS:

Protect from freezing.

Do not shake excessively.

Not for use on horizontal surfaces (floors, roofs, decks, etc.) or where water will collect.

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of Pratt & Lambert Paints. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Pratt & Lambert dealer or representative to obtain the most recent Product Data Sheet.