

# PRODUCT

---

## INFORMATION



PRATT & LAMBERT PAINTS

### PRO-HIDE<sup>®</sup> Silver Interior/Exterior Flat Wall Paint Z8101

#### DESCRIPTION:

PRO-HIDE Silver Interior/Exterior Flat Wall Paint is a quality finish designed for the demanding interior and exterior exposures in the West and Southwest regions of the U.S. It is used in new construction and on repaint applications where a flat finish and good durability is required.

#### USES:

Recommended for interior and exterior applications over properly prepared concrete, masonry, aggregate block, sheetrock, cement, primed steel and primed wood.

**SIZES:** Fives

**COLORS:** White/Base 1

#### RECOMMENDED SYSTEMS:

##### NEW WORK:

##### CONCRETE, STUCCO

1 coat of PRO-HIDE Gold Exterior Acrylic Concrete & Stucco Primer  
1 or 2 coats of PRO-HIDE Silver Int/Ext Flat Wall Paint

##### CONCRETE BLOCK, CMU, SPLIT-FACE BLOCK

1 coat PRO-HIDE Gold Exterior Acrylic Surface Conditioner  
1 or 2 coats of PRO-HIDE Silver Int/Ext Flat Wall Paint

##### INTERIOR DRYWALL

1 coat PRO-HIDE Gold Latex Wall Primer  
1 or 2 coats PRO-HIDE Silver Int/Ext Flat Wall Paint

##### EXTERIOR DRYWALL

1 coat PRO-HIDE Gold Exterior Latex Primer  
1 or 2 coats of PRO-HIDE Silver Int/Ext Flat Wall Paint

##### WOOD

1 coat PRO-HIDE Gold Interior Oil Primer (interior) or  
1 coat SUPRIME Exterior Alkyd Wood Primer (exterior)  
1 or 2 coats PRO-HIDE Silver Int/Ext Flat Wall Paint

##### STEEL

1 coat Tech-gard Alkyd Metal Primer or Tech-gard Acrylic Prime or Finish  
1 or 2 coats PRO-HIDE Silver Int/Ext Flat Wall Paint

##### REPAINT:

1 coat PRO-HIDE Gold Exterior Acrylic Surface Conditioner (exterior)  
1 coat PRO-HIDE Gold Latex Wall Primer (interior)  
1 or 2 coats PRO-HIDE Silver Int/Ext Flat Wall Paint

#### PRODUCT DETAIL:

<b>Vehicle:</b>	Vinyl Acrylic
<b>Sheen:</b>	Flat (0-5 @ 85°)
<b>% Solids:</b>	By Weight: 49% By Volume: 31%
<b>Wt./Gallon:</b>	11.29 lbs.
<b>Viscosity:</b>	92-98 Ku
<b>Flashpoint:</b>	499°F
<b>VOC Level:</b>	38g/l, 0.31 lb/gl
<b>Thinner:</b>	Water
<b>Cleanup:</b>	Water
<b>Dry Time:</b>	@ 77°F (25°C) 50% RH: To Touch: 0.5 Hours To Recoat: 2.0 Hours
<b>Rec. Film Thickness:</b>	Dry: 1.2 Mils Wet: 4.0 Mils
<b>Coverage:</b>	400 sq. ft./gallon

#### APPLICATION:

<b>Brush:</b>	Nylon/Polyester
<b>Roller:</b>	3/8" nap synthetic cover
<b>Pad:</b>	Standard
<b>Conv. Spray:</b>	Thin with up to 1 pint water per gallon
<b>Airless Spray:</b>	No reduction necessary

**Limitations:** DO NOT apply when air, surface or product temperature is below 50°F (10°C) or if temperatures might drop to this level within 4 hours after application. DO NOT paint when precipitation is imminent or very late in the day when dew is likely. Ensure temperature is 5°F above the dew point.

Technical Information Line:  
1-800-BUY-PRAT (1-800-289-7728)  
[www.prattandlambert.com](http://www.prattandlambert.com)

## SURFACE PREPARATION:

**WARNING!** Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

### General

Remove all surface contamination by washing with appropriate cleaner, rinse thoroughly and allow to dry. Scrape and sand peeled or checked paint to a sound surface. Sand glossy surfaces dull.

### Drywall

Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.

### Exterior Drywall

Fill cracks and nail holes with an exterior grade patching paste/spackle and sand smooth. Remove all sanding dust.

### Masonry, Concrete, Cement, Block, Stucco, Brick

Allow new surfaces to cure according to supplier's recommendations, or at least 7 days. Allow stucco to cure at least 30 days.

Remove all surface contamination (dirt, dust, grease, oil, peeling paint, heavy chalk, efflorescence, laitance, concrete dust, etc.) by washing with an appropriate cleaner. If necessary, pressure wash with a minimum of 2100 psi, rinse thoroughly and allow to dry.

Remove all form release and curing agents. On tilt-up and poured-in-place concrete, commercial detergents or sandblasting may be necessary to remove sealers, release compounds, and to provide an anchor pattern.

Repair or replace damaged or defective substrates as needed using proper patches and sealants. Allow brick to age for 1 year prior to coating.

If painting cannot wait 30 days, or surfaces have a pH from 9 to 13, allow surface to dry 5-7 days and use PRO-HIDE Gold Acrylic Concrete and Stucco Primer or PRO-HIDE Gold Acrylic Surface Conditioner as a first coat.

### Wood

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.

### Steel, Aluminum and Galvanized

Wash with appropriate cleaner to remove any oil, grease, or other surface contamination.

Remove all corrosion with sandpaper, steel wool, or other abrading method. Remove rust and mill scale using sandpaper, steel wool, or other abrading method. Prime bare steel the same day as cleaned.

### Caulking

Fill gaps between walls, moldings, and other trim with latex or siliconized latex caulk after priming the surface.

## CLEANUP INFORMATION:

Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of Pratt & Lambert Paints. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Pratt & Lambert dealer or representative to obtain the most recent Product Data Sheet.



## PRATT & LAMBERT PAINTS

### APPLICATION:

Apply at temperatures above 50°F.  
No reduction necessary.

#### Brush

Use a nylon/polyester brush.

#### Roller

Use a 3/8" - 1-1/2" nap synthetic roller cover.

#### Spray-Airless

Pressure ..... 2500 psi  
Tip ..... .017 - .021

#### Spray-Conventional

*Thin with up to 1 pint of water*

Air Pressure ..... 40-60 psi  
Fluid Pressure ..... 30-50 psi  
Cap/Tip ..... 704/E

### TIPS TO IMPROVE

#### PERFORMANCE:

- Clean the surface thoroughly.
- Prepare the substrate to create a uniform surface.
- Patch cracks, crevices, and through-wall openings using proper sealant or patch.
- Fill voids and openings around windows and doors using proper sealant or patch.
- Caulk as needed using quality latex or siliconized latex caulk or sealant.

#### MAINTENANCE:

To assure maximum washability and durability, wait at least two weeks before washing the dry paint film. When removing stains, dirt, and marks, use a soft cloth or sponge with water or other general purpose household cleaner. Penetrating stains and marks can be removed either by applying a solution of household bleach in water and then rinsing with clean water; or, by carefully using an abrasive cleaner and water.

#### CAUTIONS:

For interior or exterior use.  
Protect from freezing.  
Not for use on roofs, floors, or decks.  
Not for use on horizontal surfaces where water will collect.