

PRODUCT

INFORMATION



PRATT & LAMBERT PAINTS

PRO-HIDE® Bronze Interior / Exterior Latex Flat Z8480 / F8480 Series

DESCRIPTION:

PRO-HIDE Bronze Interior/Exterior Latex Flat is a good quality flat finish designed for use in new and repaint work. PRO-HIDE Bronze Interior/Exterior Latex Flat has good hiding, weather resistance and durability.

USES:

New or previously painted interior or exterior surfaces such as walls, ceilings, siding, shingles, shakes, wood, masonry and primed metal.

SIZES: Fives, Gallons

COLORS:

Pro White. May be tinted to approximate color matches using Base 1 formulas.

RECOMMENDED SYSTEMS:

NEW WORK:

WOOD

Cedar or Redwood

Spot prime knots with *SU*PRIME Int/Ext Odorless Stain Blocker

1 coat of PRO-HIDE Gold Exterior Alkyd Primer

1 or 2 coats of PRO-HIDE Bronze Interior/Exterior Latex Flat

Fiberboard, Hardboard

1 coat of PRO-HIDE Gold Exterior Alkyd Primer

1 or 2 coats of PRO-HIDE Bronze Interior/Exterior Latex Flat

VINYL OR ALUMINUM SIDING

1 or 2 coats of PRO-HIDE Bronze Interior/Exterior Latex Flat

(Do not use colors darker than the original siding color)

METAL

1 coat of Tech-gard Alkyd Metal Primer or Tech-gard Acrylic Prime or Finish

1 or 2 coats of PRO-HIDE Bronze Interior/Exterior Latex Flat

MASONRY OR AGGREGATE BLOCK

1 or 2 coats of PRO-HIDE Bronze Interior/Exterior Latex Flat

(For a filled effect, use PRO-HIDE Silver Heavy Duty Latex Block Filler as a first coat)

REPAINT:

Spot prime bare areas with appropriate primer

1 or 2 coats of PRO-HIDE Bronze Interior/Exterior Latex Flat

PRODUCT DETAIL:

Vehicle:	100% Acrylic Latex
Sheen:	Flat (0-5 @ 85°)
% Solids:	By Weight: 49% By Volume: 32%
Wt./Gallon:	11.1 lbs.
Viscosity:	94-100 Ku
Flashpoint:	499°F
VOC Level:	Max 250 g/l (2.08 lbs./gal.)
Thinner:	Thin with up to 1 pint of water per gallon.
Cleanup:	Soap and water
Dry Time:	@ 77°F (25°C) 50% RH: To Touch: 0.5 Hour Recoat: 4.0 Hours Use: 4.0 Hours
Rec. Film Thickness:	Dry: 1.3 Mils Wet: 4.0 Mils
Coverage:	400 sq. ft./gallon

APPLICATION:

Brush:	Nylon or Polyester
Roller:	3/8" nap cover
Pad:	Standard
Conv. Spray:	Thin with up to 1 pint water
Airless Spray:	At package consistency

Limitations: DO NOT apply when air, surface or product temperature is below 50°F or if temperatures might drop to this level within 48 hours after application.

Notes: Coverage figures do not include spray loss. Also allow for surface irregularities and porosity of surface to be finished.

Technical Information Line:
1-800-BUY-PRAT (1-800-289-7728)
www.prattandlambert.com

SURFACE PREPARATION:

WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.

Exterior Drywall/Drywall

Fill cracks and nail holes with an exterior grade patching paste/spackle and sand smooth. Remove all sanding dust.

Masonry, Concrete, Cement, Block, Stucco, Brick

Allow new surfaces to cure according to supplier's recommendations, or at least 7 days. Remove all surface contamination (dirt, dust, grease, oil, peeling paint, heavy chalk, efflorescence, laitance, concrete dust, etc.) by washing with an appropriate cleaner; if necessary, pressure wash with a minimum of 2100 psi, rinse thoroughly and allow to dry. Remove all form release and curing agents. On tilt-up and poured-in-place concrete, commercial detergents or sandblasting may be necessary to remove sealers, release compounds, and to provide an anchor pattern. Repair or replace damaged or defective substrates as needed.

Allow brick to weather for 1 year prior to coating.

On surfaces with a pH from 9 to 13, use Pro-Hide Gold Acrylic Concrete and Stucco Primer.

Wood

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.

Aluminum and Galvanized Steel

Wash with appropriate cleaner to remove any oil, grease, or other surface contamination. Remove all corrosion with sandpaper, steel wool, or other abrading method.

Steel

Remove rust and mill scale using sandpaper, steel wool, or other abrading method. Prime bare steel the same day as cleaned.

Vinyl

Clean the surface thoroughly by scrubbing with warm, soapy water. Rinse thoroughly.

Caulking

Fill gaps between windows, doors, trim, and other through-wall openings with latex or siliconized latex caulk after priming the surface.

Mildew

Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. **DO NOT ADD DETERGENTS OR AMMONIA TO THE BLEACH/WATER SOLUTION.**

CLEANUP INFORMATION:

Clean spills and splatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of Pratt & Lambert Paints. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Pratt & Lambert dealer or representative to obtain the most recent Product Data Sheet.



PRATT & LAMBERT PAINTS

APPLICATION:

Do not apply at air or surface temperatures below 50°F or when air or surface temperatures may drop below 50°F within 48 hours.

Brush

Use a nylon/polyester brush.

Roller

Use a 3/8" nap synthetic roller cover.

Spray—Airless

Pressure 2000 psi

Tip017 - .021

Spray—Conventional

Thin with up to 1 pint of water

Air Pressure 40-60 psi

Fluid Pressure 10-20 psi

Cap/Tip 704/E

TIPS TO IMPROVE

PERFORMANCE:

- Clean the surface thoroughly.
- Prepare the substrate to create a uniform surface.
- Patch cracks, crevices, and through-wall openings using proper sealant or patch.
- Fill voids and openings around windows and doors using proper sealant or patch.
- Caulk as needed using quality latex or siliconized latex caulk or sealant.

MAINTENANCE:

To assure maximum washability and durability, wait at least two weeks before washing the dry paint film. When removing stains, dirt, and marks, use a soft cloth or sponge with water or other general purpose household cleaner. Penetrating stains and marks can be removed either by applying a solution of household bleach in water and then rinsing with clean water; or, by carefully using an abrasive cleaner and water.

CAUTIONS:

For exterior use only.

Protect from freezing.

Not for use on roofs, floors, or decks.

Not for use on horizontal surfaces where water will collect.